

Sack Products Evaluation

Product: CleanCrete Concrete 50# Bag B1QC Book: *RD2108*

Plant: 1402

Trial Batched 7/7/2009

Mfg. Ref: 7/6/2009

Design Ref:

Visual Check: Grey powder and dry sand/aggregate mix. Even distribution - No Lumps

Wet Density: 132.2 pcf

Slump/Flow: 2.5 inches *Slump Cone*

Mix Temp: 84 degrees

Soundness: N/A

Initial Set: N/A

Final Set: N/A

Mix Proportions:**Material****Trial Amount**

Product

51.0 lbs

Water

8.4 lbs

Compressive Strength:

Cylinder

Fc (psi)

Average @ 7 days

3966

Average @ 14 days

4930

Average @ 28 days

5449

Sack Products Evaluation

Product: CleanCrete Concrete 50# Bag B3QC Book: *RD2109*

Plant: 1402

Trial Batched 7/7/2009

Mfg. Ref: 7/6/2009

Design Ref:

Visual Check: Grey powder and dry sand/aggregate mix. Even distribution - No Lumps

Wet Density: 131.4 pcf

Slump/Flow: 2 inches *Slump Cone*

Mix Temp: 84 degrees

Soundness: N/A

Initial Set: N/A

Final Set: N/A

Mix Proportions:**Material****Trial Amount**

Product

51.0 lbs

Water

7.7 lbs

Compressive Strength:

Cylinder

Fc (psi)

Average @ 7 days

3950

Average @ 14 days

4908

Average @ 28 days

5550